

## COPPERWOOD ASSAYS

GL/RM - Gray Laminated/Red Massive units

Copper-bearing sequence (CBS) - Domino + Red Massive + Gray Laminated

Total depths and thicknesses reported; beds strike ~090 and dip 7-12 degrees North; true thicknesses based on a 10 deg dip and do not account for hole deviation if inclination >80 deg

Holes prefaced by "CW" were drilled by Orvana and were subjected to Orvana's QA/QC protocol

Holes prefaced by "M" were drilled by AMAX in 1956-57 and only those holes located in the field are reported herein; selected core were resampled and assayed (February 13, 2009 press release)

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	(Mag N)		true thickness	grade thickness
								Angle	Azimuth		
CW-08-09	Hanging Wall	37.84	38.14	0.30	0.82	2.8	S Sector			0.30	0.24
	GL/RM	38.14	39.71	1.57	0.89	2.8				1.55	1.38
	Domino	39.71	41.27	1.55	2.04	3.2				1.53	3.12
<b>TOTAL - copper-bearing sequence</b>				<b>3.13</b>	<b>1.46</b>	<b>3.0</b>				<b>3.08</b>	<b>4.50</b>
CW-08-13	Hanging Wall	136.74	137.09	0.34	0.01	1.7	Central			0.34	0.00
	GL/RM	137.09	138.41	1.33	0.73	9.3				1.31	0.95
	Domino	138.41	140.35	1.94	2.90	5.2				1.91	5.52
<b>TOTAL - copper-bearing sequence</b>				<b>3.26</b>	<b>2.01</b>	<b>6.9</b>				<b>3.21</b>	<b>6.47</b>
CW-08-16	Hanging Wall	203.45	203.75	0.30	0.02	0.7	Central			0.30	0.01
	GL/RM	203.75	204.80	1.05	1.21	11.6				1.03	1.25
	Domino	204.80	206.80	2.00	2.53	3.7				1.97	4.99
<b>TOTAL - copper-bearing sequence</b>				<b>3.05</b>	<b>2.08</b>	<b>6.4</b>				<b>3.00</b>	<b>6.24</b>
CW-08-17	Hanging Wall	164.27	164.50	0.23	1.00	3.4	E sector			0.23	0.22
	GL/RM	164.50	165.82	1.33	0.95	3.4				1.31	1.24
	Domino	165.82	167.47	1.65	2.32	4.9				1.62	3.75
<b>TOTAL - copper-bearing sequence</b>				<b>2.97</b>	<b>1.71</b>	<b>4.2</b>				<b>2.93</b>	<b>5.00</b>
CW-08-20	Hanging Wall	94.44	94.74	0.30	0.62	1.9	SE sector			0.30	0.19
	GL/RM	94.74	96.11	1.37	0.84	2.7				1.35	1.13
	Domino	96.11	97.87	1.76	2.00	3.1				1.73	3.46
<b>TOTAL - copper-bearing sequence</b>				<b>3.13</b>	<b>1.49</b>	<b>2.9</b>				<b>3.08</b>	<b>4.59</b>
CW-09-21	Hanging Wall	87.8	88.1	0.3	0.95	4.3	SE sector	86.0	167	0.30	0.28
	GL/RM	88.1	89.5	1.3	0.98	4.1				1.30	1.27
	Domino	89.5	91.3	1.8	2.50	4.9				1.82	4.54
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>1.87</b>	<b>4.5</b>				<b>3.11</b>	<b>5.82</b>
CW-09-22	Hanging Wall	32.7	33.0	0.3	1.21	6.9	S edge			0.30	0.36
	GL/RM	33.0	34.3	1.3	1.15	6.4				1.33	1.53
	Domino	34.3	36.2	1.9	2.34	5.4				1.90	4.45
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.85</b>	<b>5.8</b>				<b>3.23</b>	<b>5.98</b>
CW-09-23	Hanging Wall	54.4	54.7	0.3	1.22	7.4	S edge			0.30	0.37
	GL/RM	54.7	56.0	1.3	1.20	6.8				1.25	1.50
	Domino	56.0	58.0	2.0	2.81	7.7				1.95	5.47
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.18</b>	<b>7.3</b>				<b>3.20</b>	<b>6.97</b>
CW-09-24	Hanging Wall	114.9	115.2	0.3	1.08	4.7	SE sector			0.30	0.32
	GL/RM	115.2	116.6	1.4	0.93	4.2				1.37	1.28
	Domino	116.6	118.4	1.8	2.54	5.6				1.80	4.57
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>1.85</b>	<b>5.0</b>				<b>3.16</b>	<b>5.85</b>
CW-09-25	Hanging Wall	137.6	137.7	0.2	1.10	2.9	SE sector	81.0	180	0.17	0.19
	GL/RM	137.7	139.0	1.3	1.46	3.3				1.24	1.82
	Domino	139.0	140.7	1.7	2.51	5.3				1.71	4.29
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>2.07</b>	<b>4.4</b>				<b>2.95</b>	<b>6.11</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	Angle	(Mag N)	(Assumes	grade
									Azimuth	10 deg dip)	thickness
CW-09-26	Hanging Wall	132.7	133.0	0.3	0.33	0.4	East edge	81.0	175	0.30	0.10
	GL/RM	133.0	134.4	1.5	0.92	1.1				1.45	1.33
	Domino	134.4	135.0	0.5	1.09	0.5				0.51	0.56
<b>TOTAL - copper-bearing sequence</b>				<b>2.0</b>	<b>0.96</b>	<b>0.9</b>				<b>1.96</b>	<b>1.89</b>
CW-09-27	GL/RM	not cored					SE sector	82.0	309		
	Domino	125.0	127.1	2.1	2.88	7.4				2.04	5.98
<b>TOTAL - copper-bearing sequence</b>				<b>2.1</b>	<b>2.88</b>	<b>7.4</b>				<b>2.04</b>	<b>5.98</b>
CW-09-28	Hanging Wall	137.0	137.3	0.3	0.69	2.1	East edge	81.0	182	0.30	0.21
	GL/RM	137.3	138.7	1.4	0.98	2.9				1.35	1.32
	Domino	138.7	140.1	1.4	2.29	4.1				1.41	3.24
<b>TOTAL - copper-bearing sequence</b>				<b>2.8</b>	<b>1.65</b>	<b>3.5</b>				<b>2.77</b>	<b>4.56</b>
CW-09-29	Hanging Wall	157.5	157.8	0.3	0.78	1.9	East edge	81.0	190	0.30	0.23
	GL/RM	157.8	159.2	1.3	1.02	2.5				1.31	1.34
	Domino	159.2	160.6	1.4	1.81	2.5				1.39	2.52
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>1.43</b>	<b>2.5</b>				<b>2.70</b>	<b>3.86</b>
CW-09-30	Hanging Wall	137.7	138.0	0.3	1.07	6.4	SE sector	83.0	181	0.30	0.32
	GL/RM	138.0	139.5	1.5	1.27	6.0				1.49	1.88
	Domino	139.5	141.3	1.8	2.73	6.7				1.76	4.79
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.06</b>	<b>6.4</b>				<b>3.24</b>	<b>6.67</b>
CW-09-31	Hanging Wall	181.3	181.9	0.6	1.10	1.2	East edge	82.0	189	0.60	0.66
	GL/RM	181.9	183.4	1.5	1.05	3.2				1.49	1.56
	Domino	183.4	184.3	0.9	3.43	4.5				0.93	3.19
<b>TOTAL - copper-bearing sequence</b>				<b>2.5</b>	<b>1.97</b>	<b>3.7</b>				<b>2.42</b>	<b>4.75</b>
CW-09-32	Hanging Wall	171.9	172.6	0.7	1.32	5.8	NE sector			0.68	0.89
	GL/RM	172.6	173.2	0.6	1.90	5.4				0.62	1.17
	Domino	173.2	174.8	1.7	3.37	5.6				1.64	5.52
<b>TOTAL - copper-bearing sequence</b>				<b>2.3</b>	<b>2.97</b>	<b>5.5</b>				<b>2.25</b>	<b>6.69</b>
CW-09-33	Hanging Wall	148.2	148.4	0.3	0.03	2.4	NE sector	82.0	186	0.27	0.01
	GL/RM	148.4	149.5	1.1	0.81	9.8				1.06	0.86
	Domino	149.5	151.6	2.1	3.19	7.7				2.05	6.54
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.38</b>	<b>8.4</b>				<b>3.11</b>	<b>7.40</b>
CW-09-34	Hanging Wall	263.4	263.7	0.3	0.68	3.4	N sector	89.0	131	0.30	0.20
	GL/RM	263.7	264.7	1.0	1.28	5.0				1.02	1.31
	Domino	264.7	265.9	1.2	2.42	6.3				1.19	2.87
<b>TOTAL - copper-bearing sequence</b>				<b>2.2</b>	<b>1.89</b>	<b>5.7</b>				<b>2.21</b>	<b>4.18</b>
CW-09-35A	Hanging Wall	170.0	170.3	0.3	0.01	1.2	Central	88.8	169	0.30	0.00
	GL/RM	170.3	171.5	1.2	0.94	15.0				1.19	1.13
	Domino	171.5	173.5	2.0	2.83	7.2				1.96	5.55
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.12</b>	<b>10.1</b>				<b>3.15</b>	<b>6.67</b>
CW-09-36	Hanging Wall	166.8	167.1	0.3	0.01	1.6	NE sector	88.0	182	0.30	0.00
	GL/RM	167.1	168.3	1.2	0.88	11.8				1.20	1.06
	Domino	168.3	170.2	1.9	2.93	7.8				1.92	5.62
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.14</b>	<b>9.4</b>				<b>3.11</b>	<b>6.68</b>
CW-09-37	Hanging Wall	232.7	233.0	0.3	0.01	2.0	N sector	89.0	166	0.30	0.00
	GL/RM	233.0	234.1	1.1	0.69	14.5				1.11	0.76
	Domino	234.1	235.9	1.8	2.58	10.4				1.77	4.57
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>1.85</b>	<b>12.0</b>				<b>2.88</b>	<b>5.33</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	Angle	(Mag N)	(Assumes	grade
									Azimuth	10 deg dip)	thickness
CW-09-38	Hanging Wall	not cored					S edge	83.0	192		
	GL/RM	58.0	59.9	1.9	1.19	4.9				1.92	2.29
	Domino	59.9	61.3	1.4	2.01	3.5				1.36	2.73
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.53</b>	<b>4.3</b>				<b>3.28</b>	<b>5.01</b>
CW-09-39	Hanging Wall	216.1	216.3	0.2	0.33	0.4	NE sector	90.0	154	0.22	0.07
	GL/RM	216.3	217.5	1.2	1.48	1.5				1.20	1.78
	Domino	217.5	218.3	0.8	3.76	2.1				0.76	2.87
<b>TOTAL - copper-bearing sequence</b>				<b>2.0</b>	<b>2.37</b>	<b>1.7</b>				<b>1.96</b>	<b>4.64</b>
CW-09-41	Hanging Wall	244.7	245.0	0.3	1.34	18.2	N sector	89.0	106	0.28	0.37
	GL/RM	245.0	246.1	1.1	1.42	10.2				1.09	1.55
	Domino	246.1	247.8	1.7	2.30	5.8				1.70	3.92
<b>TOTAL - copper-bearing sequence</b>				<b>2.8</b>	<b>1.96</b>	<b>7.5</b>				<b>2.79</b>	<b>5.47</b>
CW-09-42	Hanging Wall	225.7	226.0	0.3	0.46	9.1	N sector	88.0	164	0.30	0.14
	GL/RM	226.0	227.1	1.1	1.33	9.8				1.04	1.39
	Domino	227.1	228.8	1.8	2.41	3.0				1.75	4.22
<b>TOTAL - copper-bearing sequence</b>				<b>2.8</b>	<b>2.01</b>	<b>5.5</b>				<b>2.80</b>	<b>5.61</b>
CW-09-43	Hanging Wall	79.9	80.2	0.3	1.32	10.2	SE sector	88.7	151	0.30	0.40
	GL/RM	80.2	81.4	1.2	0.96	5.6				1.16	1.11
	Domino	81.4	83.3	1.9	2.53	7.7				1.89	4.77
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>1.93</b>	<b>6.9</b>				<b>3.04</b>	<b>5.88</b>
CW-09-44	Hanging Wall	199.4	199.7	0.3	0.77	0.9	E edge	86.0	186	0.30	0.23
	GL/RM	199.7	200.8	1.1	0.92	1.2				1.11	1.03
	Domino	200.8	201.5	0.7	3.88	2.6				0.72	2.78
<b>TOTAL - copper-bearing sequence</b>				<b>1.9</b>	<b>2.08</b>	<b>1.8</b>				<b>1.83</b>	<b>3.81</b>
CW-09-45	Hanging Wall	139.0	139.3	0.3	0.95	3.0	SE sector	87.4	167	0.30	0.29
	GL/RM	139.3	140.9	1.6	1.29	3.6				1.61	2.08
	Domino	140.9	142.5	1.6	2.28	3.2				1.55	3.53
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>1.77</b>	<b>3.4</b>				<b>3.16</b>	<b>5.61</b>
CW-09-46	Hanging Wall	261.9	262.2	0.3	1.17	5.1	N sector	82.2	172	0.29	0.34
	GL/RM	262.2	263.3	1.0	1.42	5.4				1.02	1.44
	Domino	263.3	264.5	1.2	2.41	4.6				1.22	2.92
<b>TOTAL - copper-bearing sequence</b>				<b>2.3</b>	<b>1.95</b>	<b>5.0</b>				<b>2.23</b>	<b>4.37</b>
CW-09-47	Hanging Wall	107.8	108.1	0.3	1.50	2.9	Central	89.3	53	0.30	0.45
	GL/RM	108.1	109.4	1.4	1.21	2.1				1.33	1.61
	Domino	109.4	111.4	1.9	2.42	2.1				1.92	4.64
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.92</b>	<b>2.1</b>				<b>3.25</b>	<b>6.25</b>
CW-09-48	Hanging Wall	78.0	78.4	0.3	1.31	4.0	SW sector	88.0	125	0.30	0.39
	GL/RM	78.4	80.5	2.1	0.93	2.2				2.11	1.95
	Domino	80.5	81.3	0.8	2.27	1.1				0.76	1.72
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>1.28</b>	<b>1.9</b>				<b>2.87</b>	<b>3.68</b>
CW-09-49	Hanging Wall	138.8	139.1	0.3	1.65	16.9	SW sector	88.2	187	0.30	0.50
	GL/RM	139.1	140.3	1.2	1.14	8.0				1.13	1.29
	Domino	140.3	141.9	1.7	2.84	5.9				1.65	4.69
<b>TOTAL - copper-bearing sequence</b>				<b>2.8</b>	<b>2.15</b>	<b>6.8</b>				<b>2.79</b>	<b>5.98</b>
CW-09-50	Hanging Wall	145.7	146.0	0.3	1.00	10.2	Central	80.8	186	0.29	0.29
	GL/RM	146.0	147.3	1.3	1.05	5.7				1.27	1.34
	Domino	147.3	149.2	1.9	3.09	3.1				1.90	5.87
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.27</b>	<b>4.2</b>				<b>3.17</b>	<b>7.22</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	(Mag N)		grade (Assumes 10 deg dip)	thickness
								Angle	Azimuth		
CW-09-51	Hanging Wall	206.6	206.9	0.3	1.18	16.6	NW sector	87.2	163	0.30	0.35
	GL/RM	206.9	208.1	1.3	1.14	8.2				1.26	1.44
	Domino	208.1	209.8	1.7	2.59	4.1				1.65	4.28
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>1.96</b>	<b>5.9</b>				<b>2.91</b>	<b>5.72</b>
CW-09-52	Hanging Wall	216.6	216.8	0.3	0.01	1.6	NE sector	88.7	213	0.28	0.00
	GL/RM	216.8	218.0	1.2	0.35	6.3				1.16	0.41
	Domino	218.0	220.0	2.0	2.98	11.9				1.96	5.84
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.00</b>	<b>9.8</b>				<b>3.12</b>	<b>6.25</b>
CW-09-53	Hanging Wall	230.6	230.9	0.3	0.02	0.8	NW sector	86.4	149	0.30	0.00
	GL/RM	230.9	233.0	2.0	1.20	9.8				1.99	2.38
	Domino	233.0	234.4	1.5	3.03	2.8				1.43	4.34
<b>TOTAL - copper-bearing sequence</b>				<b>3.5</b>	<b>1.96</b>	<b>6.9</b>				<b>3.42</b>	<b>6.72</b>
CW-09-54	Hanging Wall	196.4	196.7	0.3	0.02	1.2	NE sector	83.0	182	0.30	0.01
	twin M-62 GL/RM	196.7	197.9	1.3	0.96	16.0				1.25	1.20
	Domino	197.9	199.9	2.0	3.06	8.5				1.98	6.04
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.24</b>	<b>11.4</b>				<b>3.23</b>	<b>7.25</b>
CW-09-55	Hanging Wall	180.7	181.1	0.4	1.12	12.3	Central	88.7	159	0.40	0.45
	GL/RM	181.1	182.1	1.0	1.34	7.2				0.96	1.29
	Domino	182.1	183.8	1.7	2.43	2.8				1.64	3.98
<b>TOTAL - copper-bearing sequence</b>				<b>2.6</b>	<b>2.03</b>	<b>4.4</b>				<b>2.60</b>	<b>5.27</b>
CW-09-56	Hanging Wall	169.3	169.6	0.3	0.05	3.5	Central	81.4	191	0.30	0.01
	GL/RM	169.6	171.0	1.4	1.22	12.1				1.39	1.70
	Domino	171.0	173.1	2.1	3.06	6.6				2.07	6.32
<b>TOTAL - copper-bearing sequence</b>				<b>3.5</b>	<b>2.32</b>	<b>8.8</b>				<b>3.46</b>	<b>8.01</b>
CW-09-57	Hanging Wall	253.5	253.8	0.3	1.35	4.6	NW Sector	89.1	258	0.30	0.41
	GL/RM	253.8	255.0	1.2	1.28	3.5				1.17	1.50
	Domino	255.0	256.0	1.0	2.33	23.2				1.03	2.40
<b>TOTAL - copper-bearing sequence</b>				<b>2.2</b>	<b>1.77</b>	<b>12.7</b>				<b>2.20</b>	<b>3.89</b>
CW-09-58	Hanging Wall	184.3	184.6	0.3	0.03	2.7	NE Sector	89.0	224	0.30	0.01
	GL/RM	184.6	185.8	1.2	1.05	14.3				1.23	1.29
	Domino	185.8	187.9	2.1	2.89	6.8				2.04	5.87
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.20</b>	<b>9.6</b>				<b>3.26</b>	<b>7.17</b>
CW-09-59	Hanging Wall	83.3	83.6	0.3	0.22	7.2	SW sector	88.4	170	0.29	0.06
	GL/RM	83.6	84.8	1.2	1.14	7.0				1.17	1.33
	Domino	84.8	86.7	1.9	1.89	7.3				1.87	3.54
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>1.60</b>	<b>7.2</b>				<b>3.04</b>	<b>4.88</b>
CW-09-60	Hanging Wall	229.6	229.9	0.3	0.03	2.4	NW Sector	88.9	141	0.27	0.01
	GL/RM	229.9	231.1	1.2	1.26	13.9				1.19	1.51
	Domino	231.1	233.1	2.0	3.10	7.2				1.99	6.17
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.41</b>	<b>9.7</b>				<b>3.19</b>	<b>7.68</b>
CW-09-61	Hanging Wall	103.6	103.9	0.3	1.61	21.8	SW Sector	87.4	165	0.34	0.54
	GL/RM	103.9	105.0	1.0	1.11	6.5				1.00	1.11
	Domino	105.0	106.9	1.9	2.81	3.9				1.88	5.28
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>2.22</b>	<b>4.8</b>				<b>2.88</b>	<b>6.39</b>
CW-09-62	Hanging Wall	225.1	225.4	0.3	0.52	14.4	NW sector	89.4	265	0.29	0.15
	GL/RM	225.4	226.4	1.0	1.35	13.1				0.98	1.33
	Domino	226.4	228.1	1.7	3.09	8.0				1.72	5.31
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>2.46</b>	<b>9.8</b>				<b>2.70</b>	<b>6.64</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	Angle	(Mag N)	(Assumes	grade
									Azimuth	10 deg dip)	thickness
CW-09-63	Hanging Wall	106.2	106.8	0.5	0.01	1.0	SW sector	87.1	172	0.54	0.01
	GL/RM	106.8	107.6	0.8	0.97	15.2				0.75	0.73
	Domino	107.6	109.8	2.2	2.70	9.5				2.16	5.85
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>2.25</b>	<b>10.9</b>				<b>2.92</b>	<b>6.57</b>
CW-09-64	Hanging Wall	211.3	211.6	0.3	0.78	16.1	NW Sector	89.2	209	0.32	0.25
	GL/RM	211.6	212.8	1.2	1.34	10.5				1.16	1.55
	Domino	212.8	214.6	1.8	3.00	8.5				1.77	5.30
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>2.35</b>	<b>9.3</b>				<b>2.92</b>	<b>6.85</b>
CW-09-65	Hanging Wall	134.1	134.6	0.6	0.39	9.6	SW sector	86.9	183	0.58	0.23
	GL/RM	134.6	135.1	0.5	0.43	4.9				0.47	0.20
	Domino	135.1	137.1	2.0	2.64	10.6				1.98	5.24
<b>TOTAL - copper-bearing sequence</b>				<b>2.5</b>	<b>2.22</b>	<b>9.5</b>				<b>2.45</b>	<b>5.44</b>
CW-09-66	Hanging Wall	191.9	192.2	0.3	0.04	2.8	NW sector	89.2	238	0.26	0.01
	GL/RM	192.2	193.0	0.8	1.23	17.2				0.83	1.02
	Domino	193.0	195.3	2.2	2.69	6.1				2.21	5.93
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>2.29</b>	<b>9.1</b>				<b>3.04</b>	<b>6.95</b>
CW-09-67	Hanging Wall	107.59	107.90	0.3	0.79	2.7	SW sector	87.0	174	0.30	0.24
	GL/RM	107.90	109.71	1.8	1.03	3.9				1.78	1.83
	Domino	109.71	111.31	1.6	1.57	16.4				1.58	2.47
<b>TOTAL - copper-bearing sequence</b>				<b>3.4</b>	<b>1.28</b>	<b>9.8</b>				<b>3.36</b>	<b>4.30</b>
CW-09-68	Hanging Wall	234.7	235.2	0.5	0.03	2.7	NW sector	89.2	185	0.48	0.02
	GL/RM	235.2	236.2	1.1	1.26	13.8				1.04	1.31
	Domino	236.2	238.1	1.9	3.12	5.0				1.83	5.71
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>2.44</b>	<b>8.2</b>				<b>2.87</b>	<b>7.03</b>
CW-09-69	Hanging Wall	82.6	83.2	0.6	1.29	10.9	SW sector	87.9	155	0.60	0.77
	GL/RM	83.2	84.4	1.2	1.02	6.9				1.16	1.19
	Domino	84.4	86.6	2.2	2.07	7.0				2.16	4.48
<b>TOTAL - copper-bearing sequence</b>				<b>3.4</b>	<b>1.71</b>	<b>7.0</b>				<b>3.33</b>	<b>5.67</b>
CW-09-70	Hanging Wall	183.51	183.81	0.3	0.07	2.6	Central	88.7	156	0.30	0.02
	GL/RM	183.81	185.05	1.2	1.51	11.3				1.22	1.84
	Domino	185.05	186.91	1.9	2.50	2.7				1.83	4.58
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>2.10</b>	<b>6.1</b>				<b>3.05</b>	<b>6.42</b>
CW-09-71	Hanging Wall	166.7	167.3	0.6	0.40	0.6	SW sector	86.4	190	0.60	0.24
	GL/RM	167.3	168.6	1.3	1.48	6.8				1.29	1.91
	Domino	168.6	170.5	1.9	2.11	2.3				1.88	3.96
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>1.85</b>	<b>4.1</b>				<b>3.17</b>	<b>5.87</b>
CW-09-72	Hanging Wall	210.6	210.9	0.3	0.41	8.4	NW sector	89.9	72	0.29	0.12
	GL/RM	210.9	212.4	1.5	1.20	8.2				1.50	1.80
	Domino	212.4	214.0	1.6	3.57	2.3				1.54	5.49
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>2.40</b>	<b>5.2</b>				<b>3.04</b>	<b>7.29</b>
CW-09-73	Hanging Wall	189.79	190.18	0.4	0.04	2.9	NW sector	88.0	152	0.38	0.02
	GL/RM	190.18	191.20	1.0	0.72	9.9				1.01	0.72
	Domino	191.20	192.84	1.6	3.27	11.3				1.61	5.26
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>2.29</b>	<b>10.8</b>				<b>2.61</b>	<b>5.98</b>
CW-09-74	Hanging Wall	141.3	141.6	0.3	0.18	1.2	SW sector	88.3	157	0.30	0.05
	GL/RM	141.6	143.3	1.7	1.06	5.2				1.63	1.74
	Domino	143.3	144.9	1.6	1.96	2.3				1.57	3.08
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.50</b>	<b>3.8</b>				<b>3.20</b>	<b>4.82</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	Angle	(Mag N)	(Assumes	grade
									Azimuth	10 deg dip)	thickness
CW-09-75	Hanging Wall	170.17	170.45	0.3	0.94	6.5	NW sector	89.2	215	0.28	0.26
	GL/RM	170.45	171.76	1.3	1.29	7.5				1.29	1.66
	Domino	171.76	173.52	1.8	2.76	4.7				1.74	4.78
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>2.13</b>	<b>5.9</b>				<b>3.02</b>	<b>6.45</b>
CW-09-76	Hanging Wall	205.5	205.8	0.3	0.06	3.7	NW Sector	89.6	53	0.33	0.02
	GL/RM	205.8	207.0	1.2	1.45	5.7				1.19	1.72
	Domino	207.0	208.8	1.8	2.94	4.5				1.77	5.21
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>2.34</b>	<b>5.0</b>				<b>2.96</b>	<b>6.93</b>
CW-09-77	Hanging Wall	100.16	100.48	0.3	1.42	7.3	SW sector	89.2	167	0.32	0.45
	GL/RM	100.48	101.39	0.9	1.06	5.3				0.89	0.94
	Domino	101.39	103.14	1.8	2.24	3.9				1.73	3.87
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>1.84</b>	<b>4.3</b>				<b>2.62</b>	<b>4.82</b>
CW-09-78	Hanging Wall	163.3	163.6	0.3	1.38	20.3	Central	89.6	53	0.32	0.44
	GL/RM	163.6	164.7	1.1	1.40	5.2				1.10	1.55
	Domino	164.7	166.6	1.9	2.61	3.9				1.86	4.84
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>2.16</b>	<b>4.4</b>				<b>2.96</b>	<b>6.39</b>
CW-09-79	Hanging Wall	162.5	162.8	0.3	0.70	12.0	Central	88.8	160	0.30	0.21
	GL/RM	162.8	163.9	1.1	1.32	9.6				1.07	1.40
	Domino	163.9	165.8	1.9	2.30	3.1				1.88	4.32
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>1.94</b>	<b>5.4</b>				<b>2.94</b>	<b>5.72</b>
CW-09-80	Hanging Wall	127.6	128.0	0.3	1.24	7.8	Central	89.4	169	0.31	0.38
	GL/RM	128.0	129.2	1.2	1.16	5.9				1.22	1.42
	Domino	129.2	130.8	1.6	2.48	4.2				1.56	3.88
<b>TOTAL - copper-bearing sequence</b>				<b>2.8</b>	<b>1.91</b>	<b>5.0</b>				<b>2.78</b>	<b>5.29</b>
CW-09-81	Hanging Wall	157.8	158.1	0.3	0.99	19.3	Central	73.2	51	0.33	0.33
	GL/RM	158.1	159.5	1.4	1.04	8.1				1.38	1.44
	Domino	159.5	161.4	1.9	2.52	4.9				1.85	4.66
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.89</b>	<b>6.3</b>				<b>3.23</b>	<b>6.09</b>
CW-09-82	Hanging Wall	120.3	120.7	0.4	0.98	16.7	Central	89.2	180	0.35	0.34
	GL/RM	120.7	121.8	1.2	1.35	12.0				1.13	1.54
	Domino	121.8	127.2	5.4	2.16	4.0				5.30	11.42
<b>TOTAL - copper-bearing sequence</b>				<b>6.5</b>	<b>2.01</b>	<b>5.4</b>				<b>6.43</b>	<b>12.96</b>
CW-09-83	Hanging Wall	147.65	147.99	0.3	0.97	15.3	Central	89.3	231	0.33	0.32
	GL/RM	147.99	149.24	1.3	1.53	11.0				1.24	1.89
	Domino	149.24	151.07	1.8	2.29	3.7				1.80	4.12
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>1.98</b>	<b>6.7</b>				<b>3.03</b>	<b>6.01</b>
CW-09-84	Hanging Wall	132.0	132.3	0.3	1.46	13.8	Central	87.6	258	0.32	0.46
	GL/RM	132.3	133.4	1.1	1.10	7.0				1.10	1.21
	Domino	133.4	135.1	1.8	2.04	5.5				1.73	3.52
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>1.68</b>	<b>6.1</b>				<b>2.82</b>	<b>4.73</b>
CW-09-85	Hanging Wall	129.2	129.5	0.4	1.39	10.4	Central	89.2	22.5	0.38	0.52
	GL/RM	129.5	130.7	1.1	1.32	5.7				1.13	1.50
	Domino	130.7	132.3	1.6	1.99	1.6				1.56	3.10
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>1.71</b>	<b>3.3</b>				<b>2.69</b>	<b>4.60</b>
CW-09-86	Hanging Wall	146.6	146.9	0.3	1.19	11.5	Central	88.6	213.1	0.32	0.38
	GL/RM	146.9	148.0	1.1	1.55	8.4				1.12	1.74
	Domino	148.0	149.8	1.8	2.29	3.3				1.77	4.04
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>2.00</b>	<b>5.3</b>				<b>2.88</b>	<b>5.77</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	(Mag N)		(Assumes grade 10 deg dip)	thickness
								Angle	Azimuth		
CW-09-87	Hanging Wall	121.7	122.0	0.3	1.10	8.0	Central	87.8	194.4	0.31	0.34
	GL/RM	122.0	123.3	1.2	1.24	6.8				1.21	1.50
	Domino	123.3	124.9	1.7	2.61	4.2				1.63	4.27
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>2.03</b>	<b>5.3</b>				<b>2.84</b>	<b>5.77</b>
CW-09-88	Hanging Wall	108.2	108.5	0.3	1.31	9.5	Central	89.4	35.9	0.31	0.41
	GL/RM	108.5	109.7	1.2	1.25	8.0				1.21	1.52
	Domino	109.7	111.9	2.2	2.49	7.2				2.20	5.48
<b>TOTAL - copper-bearing sequence</b>				<b>3.5</b>	<b>2.05</b>	<b>7.5</b>				<b>3.41</b>	<b>7.00</b>
CW-09-89	Hanging Wall	48.2	48.5	0.3	1.10	2.5	S sector	89.8	215.8	0.29	0.32
	GL/RM	48.5	49.6	1.1	1.68	3.0				1.07	1.79
	Domino	49.6	51.0	1.4	1.67	1.0				1.37	2.28
<b>TOTAL - copper-bearing sequence</b>				<b>2.5</b>	<b>1.67</b>	<b>1.9</b>				<b>2.43</b>	<b>4.08</b>
CW-09-90	Hanging Wall	79.7	80.0	0.3	1.20	4.6	S sector	89.4	69.2	0.32	0.39
	GL/RM	80.0	81.4	1.4	1.30	4.5				1.36	1.77
	Domino	81.4	82.8	1.4	2.13	3.3				1.36	2.89
<b>TOTAL - copper-bearing sequence</b>				<b>2.8</b>	<b>1.71</b>	<b>3.9</b>				<b>2.72</b>	<b>4.66</b>
CW-09-91	Hanging Wall	78.3	78.6	0.3	0.98	3.8	SW sector	89.3	113.9	0.27	0.26
	GL/RM	78.6	80.8	2.2	0.78	3.2				2.17	1.69
	Domino	80.8	81.8	1.0	1.97	1.0				1.03	2.03
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.16</b>	<b>2.5</b>				<b>3.21</b>	<b>3.72</b>
CW-09-92	Hanging Wall	89.7	90.0	0.3	0.75	2.0	SE sector	89.1	245.8	0.32	0.24
	GL/RM	90.0	91.1	1.1	0.97	3.0				1.13	1.09
	Domino	91.1	92.7	1.6	2.17	4.3				1.55	3.37
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>1.66</b>	<b>3.8</b>				<b>2.68</b>	<b>4.46</b>
CW-09-93	Hanging Wall	80.6	80.9	0.3	0.95	2.6	SE sector	89.0	280.2	0.29	0.27
	GL/RM	80.9	82.3	1.4	0.94	2.2				1.41	1.32
	Domino	82.3	83.9	1.6	2.22	3.1				1.55	3.44
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>1.61</b>	<b>2.7</b>				<b>2.95</b>	<b>4.76</b>
CW-09-94	Hanging Wall	90.4	90.8	0.3	0.51	0.8	SE sector	88.9	185.0	0.33	0.17
	GL/RM	90.8	92.2	1.4	0.97	2.4				1.40	1.35
	Domino	92.2	92.8	0.6	2.11	1.5				0.60	1.26
<b>TOTAL - copper-bearing sequence</b>				<b>2.0</b>	<b>1.31</b>	<b>2.1</b>				<b>1.99</b>	<b>2.61</b>
CW-09-95	Hanging Wall	128.0	128.3	0.3	1.07	3.0	SE sector	71.0	0.2	0.30	0.32
	GL/RM	128.3	129.9	1.7	1.05	3.0				1.64	1.72
	Domino	129.9	131.7	1.7	2.05	3.4				1.71	3.49
<b>TOTAL - copper-bearing sequence</b>				<b>3.4</b>	<b>1.56</b>	<b>3.2</b>				<b>3.34</b>	<b>5.21</b>
CW-09-96	Hanging Wall	121.1	121.4	0.3	1.04	11.4	Central	89.6	285.5	0.30	0.31
	GL/RM	121.4	122.7	1.3	1.24	9.1				1.29	1.60
	Domino	122.7	124.7	2.0	2.98	5.7				1.94	5.79
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.28</b>	<b>7.1</b>				<b>3.23</b>	<b>7.39</b>
CW-09-97	Hanging Wall	126.4	126.7	0.3	1.08	13.1	Central	70.7	268.3	0.28	0.31
	GL/RM	126.7	128.1	1.4	1.32	9.4				1.32	1.74
	Domino	128.1	130.0	1.9	2.51	6.7				1.74	4.37
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.00</b>	<b>7.9</b>				<b>3.06</b>	<b>6.11</b>
CW-09-98	Hanging Wall	142.0	142.3	0.3	0.04	2.1	Central	70.2	270.4	0.27	0.01
	GL/RM	142.3	143.8	1.5	1.01	10.1				1.27	1.29
	Domino	143.8	145.7	2.0	3.22	6.9				1.73	5.58
<b>TOTAL - copper-bearing sequence</b>				<b>3.4</b>	<b>2.29</b>	<b>8.2</b>				<b>3.01</b>	<b>6.88</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	(Mag N)		(Assumes 10 deg dip)	grade thickness		
								Angle	Azimuth				
CW-09-99	Hanging Wall	190.3	190.7	0.3	0.03	3.3	Central	88.8	268.3	0.34	0.01		
	GL/RM	190.7	191.9	1.2	1.16	12.2						1.21	1.40
	Domino	191.9	193.8	2.0	2.99	4.7						1.92	5.76
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>2.29</b>	<b>7.6</b>				<b>3.13</b>	<b>7.16</b>		
CW-09-100	Hanging Wall	221.3	221.6	0.3	0.02	1.5	N sector	88.9	91.7	0.32	0.01		
	GL/RM	221.6	222.8	1.2	1.06	12.8						1.20	1.27
	Domino	222.8	224.7	1.9	2.59	4.7						1.83	4.74
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>1.98</b>	<b>7.9</b>				<b>3.03</b>	<b>6.02</b>		
CW-09-101	Hanging Wall	188.3	188.6	0.3	0.03	3.6	NE sector	73.6	228	0.27	0.01		
	GL/RM	188.6	189.8	1.2	1.24	7.1						1.22	1.51
	Domino	189.8	192.2	2.3	3.04	6.9						2.30	7.00
<b>TOTAL - copper-bearing sequence</b>				<b>3.6</b>	<b>2.42</b>	<b>7.0</b>				<b>3.52</b>	<b>8.52</b>		
M56-W11	Hanging Wall	111.2	111.9	0.7	0.01	1.3	Central			0.72	0.01		
	GL/RM	111.9	114.0	2.1	1.01	5.4		2.10	2.13				
	Domino	114.0	115.6	1.5	1.99	4.6		1.51	3.01				
<b>TOTAL - copper-bearing sequence</b>				<b>3.7</b>	<b>1.42</b>	<b>5.1</b>				<b>3.61</b>	<b>5.14</b>		
M56-W18	Hanging Wall	79.1	79.9	0.8	0.38		S sector			0.75	0.29		
	GL/RM	79.9	81.6	1.7	1.00			1.66	1.66				
	Domino	81.6	83.0	1.4	1.72			1.41	2.43				
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>1.33</b>					<b>3.07</b>	<b>4.09</b>		
M56-W22	Hanging Wall	164.4	164.9	0.5	0.05		SW sector			0.45	0.02		
	GL/RM	164.9	167.0	2.2	0.95			2.12	2.01				
	Domino	167.0	168.9	1.8	1.95			1.78	3.47				
<b>TOTAL - copper-bearing sequence</b>				<b>4.0</b>	<b>1.40</b>					<b>3.90</b>	<b>5.48</b>		
M56-W23	Hanging Wall	201.4	201.7	0.3	0.04		Central			0.28	0.01		
	GL/RM	201.7	202.8	1.1	1.31			1.09	1.43				
	Domino	202.8	205.0	2.2	2.42			2.16	5.24				
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.05</b>					<b>3.25</b>	<b>6.67</b>		
M56-W24	Hanging Wall	287.7	288.3	0.7	0.14		N sector			0.67	0.09		
	GL/RM	288.3	289.2	0.9	1.11			0.87	0.96				
	Domino	289.2	290.0	0.8	1.97			0.75	1.49				
<b>TOTAL - copper-bearing sequence</b>				<b>1.6</b>	<b>1.51</b>					<b>1.62</b>	<b>2.45</b>		
M56-W28	Hanging Wall	161.6	162.1	0.5	0.64		E sector			0.51	0.33		
	GL/RM	162.1	163.6	1.5	1.42			1.45	2.05				
	Domino	163.6	165.1	1.6	2.36			1.53	3.61				
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>1.90</b>					<b>2.98</b>	<b>5.66</b>		
M57-W46	Hanging Wall	175.2	175.5	0.3	0.44		E sector			0.30	0.13		
	GL/RM	175.5	176.7	1.3	0.63			1.24	0.78				
	Domino	176.7	176.9	0.2	1.54			0.19	0.30				
<b>TOTAL - copper-bearing sequence</b>				<b>1.5</b>	<b>0.75</b>					<b>1.43</b>	<b>1.08</b>		
M57-W48	Hanging Wall	166.3	166.6	0.3	0.63		E sector			0.32	0.20		
	GL/RM	166.6	167.8	1.2	0.97			1.19	1.16				
	Domino	167.8	168.5	0.7	2.82			0.66	1.86				
<b>TOTAL - copper-bearing sequence</b>				<b>1.9</b>	<b>1.63</b>					<b>1.86</b>	<b>3.02</b>		
M57-W49	Hanging Wall	55.8	56.4	0.7	0.38		SE sector			0.65	0.25		
	GL/RM	56.4	57.6	1.2	0.69			1.19	0.82				
	Domino	57.6	58.2	0.6	1.87			0.56	1.06				
<b>TOTAL - copper-bearing sequence</b>				<b>1.8</b>	<b>1.07</b>					<b>1.75</b>	<b>1.88</b>		

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	(Mag N)	(Assumes	grade
								Angle	10 deg dip)	thickness
M57-W52	Hanging Wall	114.5	114.8	0.3	0.82	2.1	SE sector		0.30	0.25
	GL/RM	114.8	116.3	1.5	1.01	2.2			1.47	1.48
	Domino	116.3	117.7	1.4	2.26	3.0			1.35	3.05
<b>TOTAL - copper-bearing sequence</b>				<b>2.9</b>	<b>1.61</b>	<b>2.6</b>			<b>2.82</b>	<b>4.53</b>
M57-W53	Hanging Wall	113.3	113.6	0.3	0.46		SE sector		0.30	0.14
	GL/RM	113.6	115.2	1.6	1.32				1.57	2.07
	Domino	115.2	116.9	1.7	2.51				1.66	4.16
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.93</b>				<b>3.23</b>	<b>6.23</b>
M57-W54	Hanging Wall	200.3	200.5	0.2	1.25	0.9	NE sector		0.20	0.24
	GL/RM	200.5	201.7	1.2	1.26	2.4			1.14	1.44
	Domino	201.7	202.1	0.5	2.46	2.8			0.47	1.14
<b>TOTAL - copper-bearing sequence</b>				<b>1.6</b>	<b>1.61</b>	<b>2.5</b>			<b>1.61</b>	<b>2.59</b>
M57-W58	Hanging Wall	108.3	108.8	0.5	0.05	2.7	Central		0.51	0.03
	GL/RM	108.8	110.6	1.8	1.02	9.0			1.76	1.79
	Domino	110.6	112.5	1.9	3.26	7.5			1.89	6.16
<b>TOTAL - copper-bearing sequence</b>				<b>3.7</b>	<b>2.18</b>	<b>8.2</b>			<b>3.65</b>	<b>7.95</b>
M57-W59	Hanging Wall	153.5	153.6	0.1	0.03		Central		0.14	0.00
	GL/RM	153.6	154.8	1.2	1.22				1.17	1.42
	Domino	154.8	156.7	1.9	2.74				1.88	5.14
<b>TOTAL - copper-bearing sequence</b>				<b>3.1</b>	<b>2.15</b>				<b>3.05</b>	<b>6.57</b>
M57-W62	Hanging Wall	197.0	197.2	0.3	0.08		NE sector		0.29	0.02
	GL/RM	197.2	198.5	1.3	0.72	3.9			1.24	0.90
	Domino	198.5	200.6	2.1	2.90	4.4			2.05	5.95
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>2.08</b>	<b>4.2</b>			<b>3.29</b>	<b>6.84</b>
M57-W63	Hanging Wall	235.1	235.7	0.5	0.19		NE sector		0.51	0.10
	GL/RM	235.7	236.7	1.1	1.22	0.9			1.05	1.28
	Domino	236.7	237.2	0.5	2.87	2.8			0.51	1.47
<b>TOTAL - copper-bearing sequence</b>				<b>1.6</b>	<b>1.76</b>	<b>1.5</b>			<b>1.56</b>	<b>2.76</b>
M57-W64	Hanging Wall	158.2	158.7	0.4	0.05	1.6	Central		0.42	0.02
	GL/RM	158.7	159.8	1.1	1.25	8.9			1.13	1.40
	Domino	159.8	161.3	1.5	2.97	6.3			1.50	4.46
<b>TOTAL - copper-bearing sequence</b>				<b>2.7</b>	<b>2.23</b>	<b>7.4</b>			<b>2.63</b>	<b>5.86</b>
M57-W69	Hanging Wall	160.8	161.0	0.2	0.75	2.7	Central		0.23	0.17
	GL/RM	161.0	162.5	1.4	1.36	5.4			1.41	1.91
	Domino	162.5	164.4	1.9	2.16	2.8			1.87	4.02
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.81</b>	<b>3.9</b>			<b>3.27</b>	<b>5.93</b>
M57-W72	Hanging Wall	109.4	109.8	0.4	0.03	1.9	SW sector		0.39	0.01
	GL/RM	109.8	110.8	1.0	0.92	11.6			0.98	0.90
	Domino	110.8	112.8	2.0	2.38	7.8			1.98	4.71
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>1.90</b>	<b>9.1</b>			<b>2.95</b>	<b>5.60</b>
M57-W80	Hanging Wall	42.3	42.7	0.4	0.53	0.9	S sector		0.42	0.22
	GL/RM	42.7	45.6	2.9	1.54	2.2			2.81	4.34
	Domino	45.6	45.9	0.3	2.65	0.6			0.34	0.90
<b>TOTAL - copper-bearing sequence</b>				<b>3.2</b>	<b>1.66</b>	<b>2.0</b>			<b>3.15</b>	<b>5.24</b>
M57-W108	Hanging Wall	62.9	63.2	0.3	0.35		S sector		0.32	0.11
	GL/RM	63.2	64.8	1.6	1.00				1.56	1.56
	Domino	64.8	66.5	1.7	2.25				1.68	3.77
<b>TOTAL - copper-bearing sequence</b>				<b>3.3</b>	<b>1.64</b>				<b>3.24</b>	<b>5.33</b>

Hole	Unit	From, m	To, m	Interval, m	Cu, %	Ag, ppm	Location	(Mag N)		grade (Assumes 10 deg dip) thickness	
								Angle	Azimuth		
M57-W114	Hanging Wall	61.8	62.4	0.6	0.36		S Sector			0.60	0.22
	GL/RM	62.4	64.3	1.9	1.41					1.87	2.64
	Domino	64.3	66.2	1.9	2.14					1.83	3.92
<b>TOTAL - copper-bearing sequence</b>				<b>3.8</b>	<b>1.77</b>					<b>3.70</b>	<b>6.56</b>
M57-W116	Hanging Wall	38.3	39.0	0.7	0.49	1.7	S sector			0.68	0.33
	GL/RM	39.0	40.4	1.4	0.79	2.1				1.34	1.06
	Domino	40.4	42.0	1.6	2.16	4.4				1.62	3.49
<b>TOTAL - copper-bearing sequence</b>				<b>3.0</b>	<b>1.54</b>	<b>3.4</b>				<b>2.96</b>	<b>4.55</b>
M57-W159	Hanging Wall	109.6	110.9	1.3	0.51		Central			1.32	0.68
	GL/RM	110.9	112.1	1.2	0.85					1.15	0.98
	Domino	112.1	113.1	1.0	1.78					1.02	1.81
<b>TOTAL - copper-bearing sequence</b>				<b>2.2</b>	<b>1.29</b>					<b>2.17</b>	<b>2.79</b>